



TECHNICAL DATA SHEET

| | |
|------------------------|---------------|
| Order reference | SPC150 |
| Article number | 813759 |

| | | | | | |
|-------------|---------|-----------------|---------|------------------|---|
| Date | 4-11-11 | Replaces | 7-24-03 | No. Pages | 1 |
|-------------|---------|-----------------|---------|------------------|---|

Product Description:

| | |
|-------------------------|--|
| Style | Blanket roll |
| Item Size (each) | 96 cm x 44 m |
| Color | White |
| Composition | 100% Polypropylene |
| Structure | Nonwoven mat of randomly oriented Micro-fibers [4-10 micron diameters] |
| Technology | Meltblown, 1-ply |
| Absorbency | Hydrophobic + Oleophilic |
| Bonding | Mechanical entanglement, Dimpled (no Spunbound) |

| | |
|-----------------------------|--|
| Intended Application | Chemical Resistant Sorbent BLANKET for Oil & Solvent Base Liquids |
|-----------------------------|--|

| | |
|----------------------------|--|
| Absorbency Capacity | 231 l per bale (saturated; medium viscosity-13.5x) |
|----------------------------|--|

Packaging Description:

| | | | |
|-----------------------|----------------------|-----------------|-------------------|
| Package configuration | 1 Bale | Pkg. Weight | 15.0 kg (14.8 kg) |
| Items per Package | 1-Blanket Roll /Bale | Pkg. Dimensions | 47cm dia x 97cm H |
| Container type | Polybag + Twist tie | | |

Physical Properties:

| <u>Parameter</u> | <u>SPC Test Method</u> | <u>Units</u> | <u>Nominal</u> | <u>(+/-)Tolerance</u> |
|-----------------------------|------------------------|--------------|----------------|-----------------------|
| Basis Weight | SPCTM-002 | G/M2 | 350 | 35 |
| Caliper | SPCTM-020 | mm | 6.5 | 0.6 |
| Absorbency** (med.visc.) | SPCTM-004B | gL/gS | 13.5 | 2 |
| Tensile Strength | SPCTM-007 | daN | 8.6 | 0.8 |
| Color | Visual | ----- | White | per standard |

The above properties are “nominal” values used for PROCESS CONTROL when the product is produced and/or inspected. Performance “nominals” may vary depending upon the specific application, and/or the environment being applied, stored, or shipped.

**** The "Absorbency" Spec and "SPCTM004" test method is based on the protocol of ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.**

| | |
|----------------------|--|
| Attributes | Product will be free of foreign material contamination, rips, holes, and tears. |
| Labeling | Each package to be clearly labeled with Company Name, Address, Item No., Date, and/or Package Code (Bar Code). |
| Certification | Make no changes in basic process or composition without notifying customer. Claims for non-conformance of goods must be made within 60-days of delivery. |