



**GENERAL PRODUCT SPECIFICATION**

<b>Item No.</b>	<b>AD15100-BLUE</b>
-----------------	---------------------

<b>Date</b>	3-1-2017	<b>Replaces</b>		<b>No. Pages</b>	1
-------------	----------	-----------------	--	------------------	---

**Product Description:**

<b>Style</b>	Roll
<b>Item Size (each)</b>	15" x 100'
<b>Color</b>	Gray with Black Film Backing with Adhesive
<b>Composition</b>	96-98% Polypropylene + 2-4% EMA
<b>Structure</b>	A nonwoven mat comprised of staple fibers [25-35 micron diameters] with a co-extruded chemical resistant layer with a non-skid barrier backing along with adhesive. ** The bottom layer is non-skid but not chemical resistant. The rug must be applied to a clean surface.
<b>Technology</b>	Needlepunch + Co-extruded backing
<b>Absorbency</b>	Universal ( <b>Hydrophilic</b> + Oleophilic)
<b>Bonding</b>	Mechanical needling entanglement + heat fused on 1-side + co-extrusion

<b>Intended Application</b>	Chemical Resistant Non-Skid Industrial Rug with Barrier properties for Water, Oil, or Solvent Base Liquids, with static resistant qualities.
-----------------------------	----------------------------------------------------------------------------------------------------------------------------------------------

<b>Absorbency Capacity</b>	11 gal. per bale (saturated; medium viscosity-8x)
----------------------------	---------------------------------------------------

**Packaging Description:**

Package configuration	Case	Pkg. Weight	15-lbs
Items per Package	1-Roll/case	Pkg. Dimensions	18 1/2" x 18 1/2" x 15 1/4" H
Container type	Carton		

**Physical Properties:**

Parameter	SPC Test Method	Units	Nominal	(+/-)Tolerance
Basis Weight	SPCTM-002A	G/M <sup>2</sup>	420	40
Caliper	SPCTM-003A	mils	120	10
Absorbency** (med. Oil)	SPCTM-004B	gL/gS	8	1
Tear Strength	SPCTM-006	lbs	>100	>100
Color	Visual	-----	Blue	per standard

The above properties are "nominal" values used for **PROCESS CONTROL** when the product is produced and/or inspected. Performance "nominals" may vary depending upon the specific application, and/or the environment being applied, stored, or shipped.

\*\* The "Absorbency" Spec and "SPCTM004" test method is based on the protocol of ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.

<b>Attributes</b>	Product will be free of foreign material contamination, rips, holes, and tears.
<b>Labeling</b>	Each package to be clearly labeled with Company Name, Address, Item No., Date, and/or Package Code (Bar Code).
<b>Certification</b>	Make no changes in basic process or composition without notifying customer. Claims for non-conformance of goods must be made within 60-days of delivery.

