



TECHNICAL DATA SHEET

Order reference	AW124
Article number	813791

Date	4-11-11	Replaces	6-28-06	No. Pages	1
-------------	---------	-----------------	---------	------------------	---

Product Description:

Style	SOC
Item Size (each)	7.6 cm d x 366 cm long
Color	Gray with black logo printing
Composition	Polypropylene >98%, Surfactant < 1.0%, color pigment < 0.1 %
Structure	<u>Sorbent fill:</u> Micro-fibrous meltblown polypropylene (2-10 micron diameters) <u>Outer covering:</u> Spunbond polypropylene nonwoven (15-30 micron dia. fiber)
Technology	Meltblown + Spunbond + Sealed or Enclosed ends
Absorbency	Hydrophilic + Oleophilic

Intended Application	Chemical Resistant "Universal" Sorbent Sock for Spills of Water Base, Oil Base, or Solvent Base Liquids
-----------------------------	---

Absorbency Capacity	45 l per case (saturated; medium viscosity- 9x)
----------------------------	---

Packaging Description:

Package configuration	Case	Pkg. Weight	5.3kg (4.3kg)
Items per Package	4 SOCS/Case	Pkg. Dimensions (approx.)	56.5cm x 32cm x 37.5cm
Container type	Carton		

Physical Properties:

<u>Parameter</u>	<u>SPC Test Method</u>	<u>Units</u>	<u>Nominal</u>	<u>(+/-)Tolerance</u>
SOC Weight	Gravimetric	kg	1.08	0.27
Absorbency** (med. oil)	SPCTM-012B	gL/gS	9.0	8-min.
Color	Visual	-----	Gray	per standard

The above properties are "nominal" values used for PROCESS CONTROL when the product is produced and/or inspected. Performance "nominals" may vary depending upon the specific application, and/or the environment being applied, stored, or shipped.

**** The "Absorbency" Spec and "SPCTM012" test method is based on the protocol of ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.**

Attributes Labeling	Product will be free of foreign material contamination, rips, holes, and tears. Each package to be clearly labeled with Company Name, Address, Item No., Date, and/or Package Code (Bar Code).
Certification	Make no changes in basic process or composition without notifying customer. Claims for non-conformance of goods must be made within 60-days of delivery.