



TECHNICAL DATA SHEET

Order reference	BSM3650
Article number	813838

Date	4-11-11	Replaces	6-20-06	No. Pages	1
-------------	---------	-----------------	---------	------------------	---

Product Description:

Style	Roll
Item Size (each)	91 cm x 15.24 m
Color	Gray with Black Film Backing
Composition	96-98% Polypropylene + 2-4% EMA
Structure	A nonwoven mat comprised of staple fibers [25-35 micron diameters] with a co-extruded chemical resistant layer with a non-skid barrier backing. ** The bottom layer is non-skid but not chemical resistant. The rug must be applied to a clean surface.
Technology	Needlepunch + Co-extruded backing
Absorbency	Universal (Hydrophilic + Oleophilic)
Bonding	Mechanical needling entanglement + heat fused on 1-side + co-extrusion

Intended Application	Chemical Resistant Non-Skid Industrial Rug with Barrier properties for Water, Oil, or Solvent Base Liquids, with static resistant qualities.
-----------------------------	--

Absorbency Capacity	46 l per bale (saturated; medium viscosity-8x)
----------------------------	--

Packaging Description:

Package configuration	Case	Pkg. Weight	5.4 kg (5.0kg)
Items per Package	1-Roll/Case	Pkg. Dimensions	23cm x 23cm x 94cm
Container type	Carton		

Physical Properties:

<u>Parameter</u>	<u>SPC Test Method</u>	<u>Units</u>	<u>Nominal</u>	<u>(+/-)Tolerance</u>
Basis Weight	SPCTM-002A	G/M2	360	40
Caliper	SPCTM-003A	mm	2,8	0.3
Absorbency ** (med. Oil)	SPCTM-004B	gL/gS	8	1
Tear Strength	SPCTM-006	daN	>45.4	>4.5
Color	Visual	-----	Gray/Black	per standard

The above properties are “nominal” values used for PROCESS CONTROL when the product is produced and/or inspected. Performance “nominals” may vary depending upon the specific application, and/or the environment being applied, stored, or shipped.

**** The "Absorbency" Spec and "SPCTM004" test method is based on the protocol of ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.**

Attributes	Product will be free of foreign material contamination, rips, holes, and tears.
Labeling	Each package to be clearly labeled with Company Name, Address, Item No., Date, and/or Package Code (Bar Code).
Certification	Make no changes in basic process or composition without notifying customer. Claims for non-conformance of goods must be made within 60-days of delivery.